

(12)

(21) **2 380 430**

(51) Int. Cl.⁷: **E04F 15/20, B32B 21/00**

(22) **06.11.1999**

(85) **24.01.2002**

(86) **PCT/EP99/08510**

(87) **WO01/009461**

(30) **199 36 127.4 DE 31.07.1999**

(71) **KRONOSPAN TECHNICAL COMPANY LTD.,**
Iasonos Street
1082, NIKOSIA, XX (CY).

(72)

DOHRING, DIETER (DE).
EMMLER, RICO (DE).
DEVANTIER, BERND (DE).

(74)

SHAPIRO, COHEN

(54) **REVETEMENT DE SOL LAMINE DOTE D'UNE ISOLATION SONORE CONTRE LES BRUITS DE PAS**

(54) **LAMINATE FLOORING COMPRISING TREAD SOUND-PROOFING**

(57)

The invention relates to a floor covering as is frequently used in houses and apartments. The floor covering has on its underside a layer of thermoplastic material. This layer is connected in a fixed manner to the floor covering. The floor covering consists of wood, wood derivatives and/or synthetic materials. In order to produce said floor covering, the thermoplastic material is heated and applied, or rolled onto the underside of the floor covering. The latter exhibits excellent sound-proofing properties.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2380430 A1 2001/02/08

(21) **2 380 430**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 1999/11/06

(87) Date publication PCT/PCT Publication Date: 2001/02/08

(85) Entrée phase nationale/National Entry: 2002/01/24

(86) N° demande PCT/PCT Application No.: EP 1999/008510

(87) N° publication PCT/PCT Publication No.: 2001/009461

(30) Priorité/Priority: 1999/07/31 (199 36 127.4) DE

(51) Cl.Int.⁷/Int.Cl.⁷ E04F 15/20, B32B 21/00

(71) Demandeur/Applicant:
KRONOSPAN TECHNICAL COMPANY LTD., CY

(72) Inventeurs/Inventors:
DOHRING, DIETER, DE;
DEVANTIER, BERND, DE;
EMMLER, RICO, DE

(74) Agent: SHAPIRO, COHEN

(54) Titre : REVETEMENT DE SOL LAMINE DOTE D'UNE ISOLATION SONORE CONTRE LES BRUITS DE PAS

(54) Title: LAMINATE FLOORING COMPRISING TREAD SOUND-PROOFING

(57) Abrégé/Abstract:

The invention relates to a floor covering as is frequently used in houses and apartments. The floor covering has on its underside a layer of thermoplastic material. This layer is connected in a fixed manner to the floor covering. The floor covering consists of wood, wood derivatives and/or synthetic materials. In order to produced said floor covering, the thermoplastic material is heated and applied, or rolled onto the underside of the floor covering. The latter exhibits excellent sound-proofing properties.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipo.gc.ca>

OPIC • CIPQ 191

OPIC



CIPQ

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG(19) Weltorganisation für geistiges Eigentum
Internationales Büro(43) Internationales Veröffentlichungsdatum
8. Februar 2001 (08.02.2001)

PCT

(10) Internationale Veröffentlichungsnummer
WO 01/09461 A1

- (51) Internationale Patentklassifikation⁷: E04F 15/20, B32B 21/00
- (74) Anwalt: GILLE HRABAL STRUCK NEIDLEIN
PROP ROOS; Brucknerstrasse 20, 40593 Düsseldorf (DE).
- (21) Internationales Aktenzeichen: PCT/EP99/08510
- (22) Internationales Anmeldedatum:
6. November 1999 (06.11.1999)
- (25) Einreichungssprache: Deutsch
- (26) Veröffentlichungssprache: Deutsch
- (30) Angaben zur Priorität:
199 36 127,4 31. Juli 1999 (31.07.1999) DE
- (81) Bestimmungsstaaten (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Bestimmungsstaaten (*regional*): ARIPO-Patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI-Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (71) Anmelder (*für alle Bestimmungsstaaten mit Ausnahme von US*): KRONOSPAN TECHNICAL COMPANY LTD. [CY/CY]; Iasonos Street, 1082 Nikosia (CY).
- (72) Erfinder; und
- (75) Erfinder/Anmelder (*nur für US*): DÖHRING, Dieter [DE/DE]; Mühlbacher Strasse 1, D-01561 Lampertswalde (DE). DEVANTIER, Bernd [DE/DE]; Ernst-Thälmann-Strasse 18, D-01462 Mohschatz (DE). EMMLER, Rico [DE/DE]; Striesener Strasse 38 d, D-01307 Dresden (DE).
- Veröffentlicht:
— Mit internationalem Recherchenbericht.
- Zur Erklärung der Zweibuchstaben-Codes, und der anderen Abkürzungen wird auf die Erklärungen ("Guidance Notes on Codes and Abbreviations") am Anfang jeder regulären Ausgabe der PCT-Gazette verwiesen.

(54) Title: LAMINATE FLOORING COMPRISING TREAD SOUND-PROOFING

(54) Bezeichnung: LAMINATFUSSBODEN MIT TRITTSCHALLDÄMPFUNG

(57) Abstract: The invention relates to a floor covering as is frequently used in houses and apartments. The floor covering has on its underside a layer of thermoplastic material. This layer is connected in a fixed manner to the floor covering. The floor covering consists of wood, wood derivatives and/or synthetic materials. In order to produced said floor covering, the thermoplastic material is heated and applied, or rolled onto the underside of the floor covering. The latter exhibits excellent sound-proofing properties.

(57) Zusammenfassung: Die Erfindung betrifft einen Fußbodenbelag, wie er in Häusern und Wohnungen vielfach verwendet wird. Der Fußbodenbelag weist auf seiner Unterseite eine Schicht aus thermoplastischem Material auf. Die Schicht ist fest mit dem Fußbodenbelag verbunden. Der Fußbodenbelag besteht aus Holz, Holzwerkstoffen und/oder Kunststoffen. Zur Herstellung wird das thermoplastische Material erwärmt und auf die Unterseite des Fußbodenbelages aufgestrichen oder -gewalzt. Der Fußbodenbelag weist sehr gute schalldämpfende Eigenschaften auf.

WO 01/09461 A1

Laminate floor with footstep sound absorption

The invention relates to a floor covering, as widely used in houses and apartments, and to a process for the
5 production of the floor covering.

A rigid floor covering can consist of wood, timber-based materials and/or plastics. Among other things, laminate floors are known which are composed of individual panels
10 and are laid as a floating floor. A single panel consists e.g. of an HDF support sheet and a laminate layer applied thereon, which is responsible for the appearance of the floor, among other things.

15 If people move about in a room fitted with rigid floor panels, the noise development is clearly greater than in rooms fitted with carpets or elastic floor coverings such as PVC. The noise development is based on reflections of shock waves introduced into the floor when it is walked
20 on. The amplitude spectrum of the shock or sound waves depends on the room-floor, floor-substrate boundaries and on the attenuation in the different layers. The noise development is particularly high if a layer of air remains between two layers, i.e. for example between the laminate
25 floor and the screed below it.

In order to reduce the noise development from walking, various mat-like materials, such as closed-cell polyethylene foam, cork, polymer-bonded mats of recycled
30 rubber and cork, corrugated card or soft wood-fibre fabrics are used as an underlay under a rigid floor covering above the screed. The sound-absorbing effect that can be achieved by this method is unsatisfactory, however.

Attempts have therefore already been made to stick the above mat-like materials directly to the back of a rigid floor covering, i.e. on the base of a floor panel, for example. Disadvantageously, this involves high technical complexity. The costs are consequently high. Overall, the sound reduction is unsatisfactory in relation to the technical complexity.

From the document DE 196 20 987 C1, for example, an insulating film is known, which is equipped with an adhesive strip. It is intended to stick the insulating film on to the bottom of a rigid floor covering so as to reduce noise development when the floor is walked on.

From the document DE 43 29 766 A1, it is known to provide a polymer material for the footstep sound insulation of a floor.

According to the document DE 38 35 638 A1 an insulating material made of expandable polystyrene is used as an insulating layer in rigid floor coverings.

Compared with the prior art, the object of the invention is to create a floor covering having good sound-absorbing properties, without having to deal with unreasonably high technical complexity for the purpose. A further object of the invention is to create a process by which the floor covering according to the invention can be produced by simple means.

30

The object of the invention is achieved by a floor covering having the features of the first claim. A process for the production of the floor covering has the features

of the first co-ordinated claim. Advantageous embodiments can be taken from the subordinate claims.

5 The floor covering according to claim 1 has on the bottom a layer of thermoplastic material. The layer is firmly bonded to the floor covering. The floor covering consists of wood, timber-based materials and/or plastics.

10 Thermoplastic material is one that softens and becomes free-flowing when a material-dependent temperature is exceeded. In this state, the material is deformable and can be applied to the bottom of the floor covering by spreading or roller application and thus firmly bonded to the floor covering within the meaning of the invention.

15

If the temperature falls below that mentioned above, the material solidifies and the plastic / elastic properties become evident.

20 The above properties of the thermoplastic material allow it to be firmly bonded to the bottom of the rigid floor covering by spreading or roller application at elevated temperatures. As a result of the firm bond, the sound waves are transferred directly into the sound-absorbing
25 layer without reflection at the boundary layer. Thus, a significant cause of a lack of sound absorption, which is a problem in floors according to the prior art mentioned at the beginning, is removed, resulting in substantially improved sound absorption.

30

Since the material only has to be heated and spread or rolled on, the production is simple. It is not therefore necessary to deal with high technical complexity.

The invention can, in principle, be applied to any floor covering. However, the problem according to the invention arises in particular with rigid floor coverings, such as laminate or parquet. A rigid floor covering generally
5 consists of wood, timber-based materials and/or plastics.

A thickness of the sound-absorbing layer of at least 0.1 mm has proved useful. With a 5 mm thickness of the
10 sound-absorbing layer consisting of thermoplastic material the amount of material required is in an economic ratio to the effect that can be achieved. In tests, a thickness of 0.7 mm has proved advantageous.

15 The most suitable layer thickness naturally depends on the material. It therefore varies in each individual case.

Polymers or copolymers in particular are provided as the thermoplastic material. Those polymers or copolymers
20 displaying a marked physical relaxation behaviour in the ambient temperature range are to be preferred. Examples of thermoplastic polymers with marked physical relaxation behaviour in the ambient temperature range are polyvinyl propionate or polyvinyl acetate. On the other hand
25 polycarbonate, for example, with its high glass transition temperature, is a completely unsuitable material. In terms of metrology, suitable materials display a distinct maximum e.g. when the torsion modulus is presented as a function of the temperature in the loss modulus $\tan \delta$ in
30 the ambient temperature range or immediately adjacent temperature ranges. The physical bases, including examples of curves, are contained in polymer physics text books, such as e.g.: Chemie, Physik und Technologie der

Kunststoffe vol. 6, Kunststoffe 1 - Struktur und physikalisches Verhalten der Kunststoffe -, chapter 4; K. A. Wolf, Springer-Verlag 1962.

- 5 If the material displays a marked physical relaxation behaviour in the ambient temperature range, particularly good absorption is achieved since kinetic energy is converted to heat particularly well.

- 10 Examples of materials displaying particularly good relaxation behaviour at ambient temperature are:

Polyvinyl formals, polyvinyl butyrals, polyvinyl ethers, polyisobutenes or copolymers, such as e.g. terpolymers of
15 acrylonitrile, butadiene and styrene (ABS), copolymers of vinyl chloride and 2-ethylhexyl acrylate, copolymers of vinyl acetate and vinyl laurate or polymer blends of these polymers, including with the addition of typical polymer plasticisers.

20

- A further improved sound-absorbing effect is achieved by adding fillers, especially light organic fillers with a density of less than 1 g/cm³, such as e.g. wood flour, to polymers or copolymers. These fillers can be added in
25 quantities of up to 90 wt.%. An addition of at least 10 wt.% is advantageous. In particular, 30 wt.% should be added.

- In another advantageous embodiment of the invention, the
30 thermoplastic material is selected such that it exhibits adhesive properties. Adhesion is a technical term typical of polymers. Thermoplastic rubbers are an example of a

material exhibiting adhesive properties within the meaning of the invention.

If the material is selected such that it exhibits adhesive
5 properties, it sticks to the floor substrate. The adhesion is preferably designed in such a way that the floor covering can be removed again without complex technical resources. An intermediate layer (air layer) between the floor substrate and the thermoplastic layer is minimised
10 in this way. Sound is therefore absorbed in a further improved manner.

The floor covering according to the claims is produced in that thermoplastic material is heated in such a way that
15 it becomes free-flowing. The heated material is applied to the bottom of elements of the floor covering or on to a support sheet for such a floor covering by spreading or roller application. The floor elements or the support sheet are then cooled together with the applied
20 thermoplastic material.

The invention is explained in more detail by means of the following embodiment. A floor panel in a 1285 x 185 x 8 mm format is provided as the rigid floor covering. This
25 consists of a 0.8 mm thick high pressure laminate layer, a 6.4 mm thick HDF support sheet with a density of 870 kg/m³ and a 0.8 mm thick high pressure laminate balancing layer. A thermoplastic layer consisting of a copolymer is applied to the floor panel by means of spreading equipment on the
30 back of the panel at a temperature of 150°C. The copolymer consists of vinyl acetate with an acrylate proportion of 12 wt.%. The thickness of the applied layer is 0.7 mm.

In an acoustic test chamber, the sound level was measured when a laid area of 20 m² of the floor produced according to the invention was walked on, compared with an untreated area. A closed-cell foam mat consisting of polyethylene in a thickness of 3 mm was laid under the untreated floor. The coated floor was laid without any additional insulating materials. In the result of the sound measurements, a sound level of 78 dB was detectable for the untreated floor in the measuring chamber and for the floor fitted with sound absorption according to the invention a sound level of 67 dB with the same mechanical stimulus. Since at the same time a frequency shift from higher to lower tones took place, the treated floor was perceived as substantially quieter.

Claims

1. Floor covering with a layer which is firmly bonded to the bottom of the floor covering and which consists of thermoplastic material.
2. Floor covering according to claim 1, in which the layer consisting of thermoplastic material is 0.1 to 5 mm thick.
3. Floor covering according to claim 1 or 2, in which the thermoplastic material displays a marked physical relaxation behaviour at ambient temperature.
4. Floor covering according to claim 1, 2 or 3, in which polyvinyl formals, polyvinyl butyrals, polyvinyl ethers, polyisobutenes, copolymers such as terpolymers of acrylonitrile, butadiene and styrene (ABS), copolymers of vinyl chloride and 2-ethylhexyl acrylate, copolymers of vinyl acetate and vinyl laurate or blends of these polymers, including with the addition of typical polymer plasticisers, are used as the thermoplastic material.
5. Floor covering according to one of the preceeding claims, in which polymers or copolymers with fillers, preferably light organic substances, are provided as the thermoplastic material.
6. Floor covering according to one of the preceeding claims, in which a thermoplastic material with adhesive properties is used.

7. Floor covering according to one of the preceeding claims, in which laminate is provided as the floor covering.
- 5 8. Floor covering according to one of the preceeding claims, in which the floor covering consists of wood, timber-based materials and/or plastics.
- 10 9. Process for the production of a floor covering according to one of the preceeding claims, in which thermoplastic material is heated and applied to the bottom of a floor covering by spreading or roller application.

Claims (Amended claims)

1. Floor covering with rigid laminate or parquet panels consisting of wood or timber-based materials with a layer which is firmly bonded to the bottom of the panels,

characterised in that

the layer consists of thermoplastic material, and in which the thermoplastic material is applied to the bottom of the panels without the inclusion of air.

2. to 6. as originally filed.

7. Floor covering according to one of the preceeding claims, in which the panels are thicker than the layer consisting of thermoplastic material.
8. Floor covering according to one of the preceeding claims, which can be produced by spreading or rolling the thermoplastic material in the free-flowing state on to the bottom of the floor panels.
9. Process for the production of a floor covering according to one of the preceeding claims, in which thermoplastic material is heated and applied in the free-flowing state on to the bottom of floor panels by spreading or roller application without the inclusion of air.